

## PRODUCT DESCRIPTION

TREMproof 201/60 is a high solid, VOC compliant, bitumen modified polyurethane waterproofing membrane. It is a one-part, moisture curing elastomer available in two viscosities; Self-Leveling (SL) and Roller (R) that are suitable for applications to horizontal and vertical surfaces at 1.5mm WFT (wet film thickness). Typical project application thickness is 1.2 - 1.5mm, please contact us for a project specification. When applied, the dry film thickness is typically 1mm.

Tremco Anti-Root Additive is available for use with TREMproof 201/60 as an optional feature to prohibit growing roots from affecting the overall performance of the waterproofing membrane.

## BASIC USES

TREMproof 201/60 is suited for waterproofing in plaza decks, roof terraces, pedestrian concourses, podiums, toilets, kitchens, parking garages, planter boxes, backfilled walls, basement walls and split slabs, primarily on concrete and masonry.

## FEAUTES & BENEFITS

- 1.5 mm can be applied in one coat
- High elongation and elastomeric properties lead to excellent crack-bridging ability
- No primer required on clean dry concrete
- When used with TREMproof Anti-Root Additive will inhibit root penetration through the cured membrane

## APPLICABLE STANDARDS

Conforms to ASTM C 836

## COVERAGE

TREMproof 201/60, when applied at the recommended wet film thickness of 1.5mm or 60 mils, will cover 0.67 m<sup>2</sup> per litre (1.5 litres/ m<sup>2</sup>). Coverage will vary with surface condition.

## PACKAGING

18.9L Pails

## SHELF LIFE

12 months shelf life in unopened containers when properly stored.

## APPLICATION

Even though TREMproof 201/60 is a single component product it still requires some mixing to make sure that any liquid separation that may have occurred during shipping or storage is eliminated. Before use, mix the TREMproof 201/60 using a slow speed, high torque drill equipped with a jiffy type mixing paddle for 2-3 minutes. Take care to keep the paddle submerged in the liquid during mixing. Raising the paddle in and out of the liquid can introduce air into the coating which can lead to pinholes in the cured coating.

Refer to the appropriate method statement for the system being installed for the required application techniques, application rates, etc. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Asia Technical Service for site conditions requirements.

## LIMITATIONS

- Not for use in submerged or gas vapour conditions
- Do not apply to damp or contaminated surfaces
- Not to be used as an exposed or wearing surface
- Not approved for direct contact with asphalt based

## PHYSICAL PROPERTIES

Property	Test Method	Typical Value
Ultimate Elongation	ASTM D412: 2006	> 950%
Ultimate Tensile Strength	ASTM D412: 2006	> 2.0 N/mm <sup>2</sup>
Recovery from 350% Elongation	ASTM D412: 2006	95%
Tensile at 100% Elongation	ASTM D412: 2006	> 0.8 N/mm <sup>2</sup>
Adhesion in peel after water immersion (unprimed)	ASTM C836	> 1.2 KN/m
Tear Resistance	ASTM D624: 2007	> 25 N/mm
Adhesion to Substrate	ASTM D4541: 2009	0.5 N/mm <sup>2</sup>
Shore 'A' Hardness	ASTM D2240: 2005	> 23
Shore 00 Hardness	ASTM C836	> 86
Water Vapour Transmission (average)	ASTM E96/E96M: 2010	0.2 g/h*m <sup>2</sup>
Total Water Absorption (average)	ASTM D570: 2005, 6 months at 25°C	< 5.0 %
Water Tightness	BS EN 1928: 2000	No dampness at underside of substrate
Extensibility After Heat Aging (maximum crack bridging)	ASTM C836	> 6.4 mm
Depth of penetration of water under pressure	BS EN 12390 -Part 8	Nil Penetration
Low Temperature Elongation at -29°C	ASTM D412	450%
Service Temperature (continuous ambient)	-	- 40°C to + 66°C

## STORAGE CONDITIONS

- Recommended storage conditions are indoors in a ventilated, dry area removed from heat, open flame, ignition sources and direct sunlight. Storage temperatures should range from 15 to 21°C and must not drop below 0°C or exceed 43°C.
- On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.
- Shelf life could be affected if the product is not stored properly.

## TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact StonCor Middle East to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to StonCor Middle East Quality Control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. Prices and cost data, if shown, are subject to change without prior notice. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY STONCOR MIDDLE EAST, EXPRESS OR IMPLIED, STATUTORY BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.